




Sound Absorption Graph

The following values reflect the acoustic properties of the product as tested in accordance with ASTM C423-09a.



200	250	315	400	500	630	800	1000	1250	1600	2000	2500	NRC	SAA
0.57	0.63	0.84	0.93	1.04	1.12	1.21	1.23	1.24	1.21	1.17	1.14	1.00	1.03